



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁴ : B65D 65/40, B32B 27/32	A1	(11) International Publication Number: WO 89/ 02859 (43) International Publication Date: 6 April 1989 (06.04.89)
(21) International Application Number: PCT/GB88/00806 (22) International Filing Date: 30 September 1988 (30.09.88) (31) Priority Application Number: 8723322 (32) Priority Date: 5 October 1987 (05.10.87) (33) Priority Country: GB (71) Applicant (for all designated States except US): COUR- TAULDS FILMS & PACKAGING (HOLDINGS) LTD [GB/GB]; Bath Road, Bridgwater, Somerset TA6 4PA (GB). (72) Inventor; and (75) Inventor/Applicant (for US only) : DEAN, Darren, Willi- am [GB/GB]; 65 Oakgrove Way, Beechwood Park Es- tate, Bridgwater, Somerset (GB). (74) Agent: CLAISSE, John, Anthony; Patent Department, Courtaulds Films & Packaging (Holdings) Ltd, Bath Road, Bridgwater, Somerset TA6 4PA (GB).		(81) Designated States: AT (European patent), AU, BE (Eu- ropean patent), CH (European patent), DE (Euro- pean patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European pa- tent), NL (European patent), SE (European patent), US. Published <i>With international search report.</i>
(54) Title: POLYMERIC FILM (57) Abstract The invention concerns polymeric films including a layer of polypropylene homopolymer with a layer of voided polypropylene on one side and a layer of a printable polymer on the other side. The printable polymer is preferably an ac- rylic polymer, a co- or terpolymer containing units derived from at least two of ethylene, propylene or but-1-ene, and/or a linear low density polyethylene. Films of the present invention have good gloss combined with printability and a pearles- cent effect. They can also provide evidence of tampering with packaged goods.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

Polymeric Films

This invention concerns polymeric films, and in particular polypropylene films.

It is known to form films from polypropylene which consist of a layer of polypropylene homopolymer on a layer of voided polypropylene. Such films can be produced by coextruding a layer of polypropylene homopolymer with a layer of polypropylene homopolymer containing a voiding agent, for example particulate chalk, and thereafter biaxially orienting the coextruded structure, for example using rolls rotating

- 2 -

at different speeds in the direction of extrusion and using a stenter in the direction perpendicular thereto. The resultant films have a surface gloss when viewed from the side of the unvoided homopolymer layer, particularly when the homopolymer layer is relatively thick. However, homopolymer layers have poor ink receptivity and this makes them unsuitable for use as packaging materials which require printed indicia.

Printable polymer layers with good gloss can be provided by a relatively thick layer of a copolymer on a voided polypropylene layer, but such copolymer layers are expensive.

According to the present invention there is provided a polymeric film comprising a layer of propylene homopolymer having a layer of voided polypropylene on one side and a layer of a printable polymer on the other side.

The layer of propylene homopolymer is preferably from 2.5 to 25 microns thick, more preferably from 10 to 25 microns thick, and advantageously about 22 microns thick.

The voided polypropylene layer is preferably from 5 to 25 microns thick, more preferably from 10 to 25 microns thick, and advantageously about 22 microns

thick.

The printable polymer layer will in general be considerably thinner than either the layer of homopolymer or the layer of voided polypropylene. The printable polymer layer will, however, usually be at least 0.1, more particularly at least 0.4 microns thick. Preferably such layers are up to 5 microns thick.

The polymer used to form the printable layer can be selected from those known in the art. Acrylic polymers can be used, for example random terpolymers of methyl acrylate, methyl methacrylate and methacrylic acid, or random interpolymers of styrene, butyl acrylate, methyl methacrylate and methacrylic acid. Alternatively, co- and ter-polymers containing units derived from two or more of ethylene, propylene, but-1-ene, acrylic esters, maleic anhydride and acrylic acid can be used, if desired in admixture, and/or a linear low density polyethylene.

If desired, the voided polypropylene layer can have one or more further polymeric layers thereon to provide four or five layer structures. A further polymeric layer can be provided, for example to give heat sealability and/or printability to the surface of

the film opposite the layer of printable polymer on the homopolymer layer. Suitable polymers for providing heat sealability include co- or ter-polymers containing units derived from at least two of ethylene, propylene and but-1-ene and/or a linear low polyethylene. A further polymeric layer can additionally or alternatively be provided which contains a pigment, for example to increase the opacity of the film. The pigment can, for example, be titanium dioxide. The pigmented polymer can, for example, be a propylene copolymer layer. While further printable and/or heat sealable layers will be provided as an outer layer, pigmented layers can be provided on either side of the voided layer, that is between the homopolymer and voided layers or on the voided layer opposite the homopolymer layer. If desired, a layer of a soft polymer can be provided beneath an outer heat sealable layer for improving the heat seal characteristics of the heat sealable layer. Suitable soft polymers are known in the art.

The further polymeric layer or layers are preferably from 0.5 to 5 microns thick, more preferably from 1 to 2.5 microns thick.

Films of the present invention can be

- 5 -

produced by known methods. For example, a layer of a printable polymer, a layer of a propylene homopolymer, and a layer of polypropylene containing a voiding agent can be coextruded, and the resultant composite film can then be oriented by stretching, preferably biaxially. The printable polymer in such a method is preferably a co- or ter-polymer and/or a linear low polyethylene referred to above. The preferred thickness of the resultant printable layer is 1 to 2.5 microns.

In an alternative and preferred method, the layers of propylene homopolymer and voided polypropylene are formed by coextruding a layer of the propylene homopolymer and a layer of polypropylene containing a voiding agent, and the resultant two-layer film is oriented biaxially, the printable layer being applied to the two-layer film between orientation in one direction and the other. This method has been used to produce printable layers of acrylic polymers, the polymer being applied to the two-layer film as an aqueous dispersion using a gravure roller. The dispersions preferably contain an anti-block agent, for example as is known in the art. Printable layers applied between the two stages of orientation will usually be from 0.1 to 2 microns thick, preferably

- 6 -

from 0.3 to 0.6 microns thick.

When a further polymeric layer is present, it can be formed in known manner, for example by coextrusion with the layer of propylene homopolymer and the layer of polypropylene containing the voiding agent.

The voiding agent can be selected from those known in the art, for example inorganic fillers, e.g. chalk, silicon or clays, or organic fillers, e.g. nylons or polyesters.

The amount of voiding agent present in the polypropylene layer, in combination with the degree of orientation, will determine the density of the voided layer. The voiding agent will usually be present in an amount of from 4 to 25 weight per cent based on the weight of the voided layer. When chalk is used as the voiding agent it is preferably present in an amount of from 15 to 25 weight per cent based on the weight of the voided layer. However, while any amount of voiding agent can be used which provides the desired voiding effect on stretching, it is preferred that the film produced has a density of not more than 0.71 g/cm^3 , e.g. by the use of from 15 to 25 weight per cent of chalk.

- 7 -

The present invention provides films having good gloss in combination with printability and usually with a pearlescent effect. The opacity of the film tends to increase with higher filler loadings, e.g. at above 15 weight per cent.

In a preferred aspect of the present invention, films of the present invention can also be used as tamper evident packaging materials. This latter effect can be achieved by sealing the voided polypropylene layer of a film of the present invention to itself or to another film, for example using the further polymeric layer referred to hereinbefore using heat seal or cold seal methods. The tamper evident effect is in general more apparent the lower the density of the voided layer, and it is preferred that the voided layer has a density of not more than 0.5 g/cm³. Chalk contents for the voided layer are preferably from 20 to 25 per cent by weight to produce a good tamper evident seal. Evidence of tampering is usually shown by separation of the voided layer from the propylene homopolymer layer.

The following Example is given by way of illustration only. All parts are by weight unless

- 8 -

stated otherwise.

EXAMPLE

A four layer polymeric web was produced by co-extruding at 240°C a layer of unfilled polypropylene homopolymer with a layer of polypropylene homopolymer containing about 6 per cent by weight of chalk as a voiding agent, two layers of ethylene/propylene copolymer being co-extruded to form the outer surfaces of the web.

The web was extruded on to a chill roll and then stretched 4.5:1 in the machine direction at a temperature of 120°C, and thereafter it was stretched 9.5:1 in the transverse direction in a stenter at 160°C.

The resultant oriented film consisted of a non-voided homopolymer layer 20 microns thick and a voided layer 20 microns thick, with outer copolymer layers each 1.5 microns thick. The density of the film was 0.69g/cm³.

The film had good hot tack and it was heat sealable to itself. The surface of the film having the layer of non-voided homopolymer immediately beneath

- 9 -

the printable copolymer layer had a high gloss of over 80 sheen gloss units.

The film was also provided with a cold seal coating and a satisfactory cold seal was achieved.

CLAIMS

1. A polymeric film comprising a layer of propylene homopolymer having a layer of voided polypropylene on one side and a layer of a printable polymer on the other side.
2. A film according to claim 1, wherein the layer of propylene homopolymer is from 5 to 25 microns thick.
3. A film according to claim 1 or claim 2, wherein the layer of voided polypropylene is from 5 to 25 microns thick.
4. A film according to any of the preceding claims, wherein the printable polymer is an acrylic polymer.
5. A film according to claim 4, wherein the layer of printable polymer is from 0.1 to 2 microns thick.
6. A film according to any of claims 1 to 3, wherein the printable polymer comprises a co- or ter-polymer containing units derived from at least two of ethylene, propylene or but-1-ene and/or a linear low density polyethylene.

7. A film according to claim 6, wherein the layer of printable polymer is from 0.5 to 5 microns thick.

8. A film according to any of the preceding claims, wherein the voided layer contains from 4 to 25 weight per cent of voiding agent, based on the weight of the voided layer.

9. A film according to claim 8, wherein the voided layer contains from 20 to 25 weight per cent of voiding agent, based on the weight of the voided layer.

10. A film according to any of the preceding claims, having a density of not more than 0.71 g/cm³.

11. A film according to any of the preceding claims, wherein the layer of voided polypropylene has a further polymer layer thereon.

12. A film according to any of claims 1 to 10, wherein the further polymer layer is printable and/or heat sealable.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 88/00806

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) * According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁴ : B 65 D 65/40; B 32 B 27/32											
II. FIELDS SEARCHED <div style="text-align: right; font-size: small;">Minimum Documentation Searched ⁷</div> <table style="width: 100%; border: none;"> <tr> <td style="width: 20%; border: none;">Classification System</td> <td style="border: none;">Classification Symbols</td> </tr> <tr> <td style="border: none; vertical-align: top;">IPC⁴</td> <td style="border: none; vertical-align: top;">B 32 B</td> </tr> </table> <div style="text-align: center; font-size: x-small; margin-top: 10px;"> Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸ </div>			Classification System	Classification Symbols	IPC ⁴	B 32 B					
Classification System	Classification Symbols										
IPC ⁴	B 32 B										
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹ <table border="1" style="width: 100%; border-collapse: collapse; font-size: x-small;"> <thead> <tr> <th style="width: 10%;">Category ⁹</th> <th style="width: 70%;">Citation of Document, ¹¹ with Indication, where appropriate, of the relevant passages ¹²</th> <th style="width: 20%;">Relevant to Claim No. ¹³</th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US, A, 4578297 (G.L. DUNCAN) 25 March 1986 see column 6, example 1 --</td> <td style="text-align: center; vertical-align: top;">1</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US, E, 30805 (R.R. RHOADS) 24 November 1981 see column 3, lines 1-4; column 4, lines 2-22 -----</td> <td style="text-align: center; vertical-align: top;">1</td> </tr> </tbody> </table>			Category ⁹	Citation of Document, ¹¹ with Indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³	A	US, A, 4578297 (G.L. DUNCAN) 25 March 1986 see column 6, example 1 --	1	A	US, E, 30805 (R.R. RHOADS) 24 November 1981 see column 3, lines 1-4; column 4, lines 2-22 -----	1
Category ⁹	Citation of Document, ¹¹ with Indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³									
A	US, A, 4578297 (G.L. DUNCAN) 25 March 1986 see column 6, example 1 --	1									
A	US, E, 30805 (R.R. RHOADS) 24 November 1981 see column 3, lines 1-4; column 4, lines 2-22 -----	1									
<div style="display: flex; justify-content: space-between; font-size: x-small;"> <div style="width: 45%;"> <p>* Special categories of cited documents: ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 50%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p> </div> </div>											
IV. CERTIFICATION <table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;"> Date of the Actual Completion of the International Search <div style="text-align: center; font-size: large;">2nd January 1989</div> </td> <td style="width: 50%; border: none; vertical-align: top;"> Date of Mailing of this International Search Report <div style="text-align: center; font-size: large;">17. 01. 89</div> </td> </tr> <tr> <td style="width: 50%; border: none; vertical-align: top;"> International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </td> <td style="width: 50%; border: none; vertical-align: top;"> Signature of Authorized Officer <div style="text-align: center;"> <div style="text-align: right; font-weight: bold;">P.C.G. VAN DER PUTTEN</div> </div> </td> </tr> </table>			Date of the Actual Completion of the International Search <div style="text-align: center; font-size: large;">2nd January 1989</div>	Date of Mailing of this International Search Report <div style="text-align: center; font-size: large;">17. 01. 89</div>	International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center;"> <div style="text-align: right; font-weight: bold;">P.C.G. VAN DER PUTTEN</div> </div>					
Date of the Actual Completion of the International Search <div style="text-align: center; font-size: large;">2nd January 1989</div>	Date of Mailing of this International Search Report <div style="text-align: center; font-size: large;">17. 01. 89</div>										
International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center;"> <div style="text-align: right; font-weight: bold;">P.C.G. VAN DER PUTTEN</div> </div>										

ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.

GB 8800806
SA 24561

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on 11/01/89
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4578297	25-03-86	None	
US-E- 30805	24-11-81	None	